

## Light Reflectance Values Par-ky

Measured using the Datacolor CHECK 3 spectrophotometer

Product	Grade	Color	LRV- value	Standard Deviation
European oak	Premium	light brown	32	4,0
European oak	Rustic	light brown	34	4,5
Essence oak	Premium	light brown	32	4,0
Essence oak	Rustic	light brown	34	5,0
Ivory oak	Premium	light brown	34	3,5
Ivory oak	Rustic	light brown	35	3,0
Umber oak	Premium	light brown	26	2,0
Umber oak	Rustic	light brown	24	3,0
Milk oak	Premium	white	44	4,0
Milk oak	Rustic	white	43	4,0
Desert oak	Premium	light brown	30	3,5
Desert oak	Rustic	light brown	33	1,0
Manhattan oak	Premium	brown	22	1,5
Antique oak	Premium	dark brown	13	2,0
Chocolate oak	Premium	very dark brown	5	0,9

Crystal oak	Premium	white	47	2,0
Cliffside oak	Premium	light brown	30	2,5
Canyon oak	Premium	brown	27	2,0
History oak	Rustic	brown	13	3,0
Smoked walnut		dark brown	11	1,5
Cotton Triba		white	45	1,0
Afrormosia		dark brown	10	0,6
Teak		brown	15	3,0
Shadow Macassar		dark brown	6	2,0
Rosewood santos		brown	14	6,5
Bamboo steamed		light brown	25	4,5
Jatoba		red brown	9	3,0